

Scott Bader - CrusticROOF Topcoat

**NORTHEAST
ROOFING LTD**

www.neroofting.co.uk

CrysticROOF Topcoat

ISO Topcoat for Brush or Roller Application

Introduction

CrysticROOF Topcoat is a pre-accelerated isophthalic topcoat. It has been formulated for brush or roller application.

The Scott Bader Technical Service Department is able to provide information and advice relating to the use of composites products in a wide range of markets and applications.

Applications

Crystic CrysticROOF Topcoat is suitable for use in general flat roofing applications.

Features and Benefits

CrysticROOF Topcoat has been developed to ensure good intrinsic weathering properties and good water resistance. The robust formulation ensures the topcoat is suitable for use in a wide range of application conditions.

Product Characteristics

CrysticROOF Topcoat should be allowed to attain workshop temperature (18°C - 25°C) before use. Stir well by hand, or with a low shear mixer to avoid aeration, and then allow to stand to regain thixotropy. CrysticROOF Topcoat requires only the addition of a catalyst to start the curing reaction. The recommended catalyst is Catalyst M (or Butanox M50), which should be added at 2 % into the gelcoat. (Please consult our Technical Service Department if other catalysts are to be used). The catalyst should be thoroughly incorporated into the topcoat, with a low shear mechanical stirrer where possible. Please consult our Technical Service Department for further application advice.

For normal use, the application of CrysticROOF Topcoat should be controlled to 0.4 - 0.5 mm (0.015 - 0.020 inch) wet film thickness. As a guide, approximately 650-800 g/m² of topcoat mixture (depending on pigment) will give the required thickness when evenly applied. CrysticROOF Topcoat should be applied to clean and dry surfaces and when used outside when rain is not likely to fall within 2 hours of application.

Properties

Typical Properties

The following table gives typical liquid properties of CrysticROOF Topcoat when tested in accordance with Scott Bader test methods.

Properties for CrysticROOF Topcoat	Method	Typical Result
Viscosity, 25 °C 0.6s ⁻¹	3.41	250-350 poise
Viscosity, 25 °C 4500s ⁻¹	3.6	4 – 8 poise
Specific gravity @ 25 °C	-	1.7
Stability in the dark @ 20 °C	-	3 months
Geltime 20 °C 2% Catalyst M (Butanox M50)	5.25	7 – 12 minutes

Storage

CrysticROOF Topcoat should be stored in the original containers which must be kept closed and airtight. It is recommended that the storage temperature should be less than 20°C to achieve maximum storage life.

Packaging

CrysticROOF Topcoat is supplied in 20kg and 225kg containers.

Health And Safety

Please refer to Material Safety Data Sheet.

May 2000



Scott Bader Company Limited

Wollaston, Wellingborough,
Northamptonshire NN29 7RL
Telephone: +44 (0) 1933 663100
Facsimile: +44 (0) 1933 666139
www.scottbader.com



CONTACT:

SOUTH SHIELDS:

12 Mackley Close
South Shields
NE34 0LJ

Tel: 0191 206 9710

BISHOP AUCKLAND:

98 William Street
Bishop Auckland
DL14 8RJ

Tel: 01388 326 039

EAST MIDLANDS:

Tel: 07565 581 889

Email: info@neroofting.co.uk

Website: www.neroofting.co.uk

**NORTHEAST
ROOFING LTD**